



TECHNICAL DATA SHEET DCS147 – X60

(Dorsa Chemie Short Oil Alkyd Resin)

DESCRIPTION:

DCS147 – X60 is a Short-Oil, Fast air-drying Alkyd Resin based on Soya bean oil.

PROPERTIES:

Excellent surface hardness, Excellent none-yellowing ,very fast surface and deep drying , good weather resistance, excellent adhesion to metal and wood, good Elasticity and plasticizing properties. very good pigment wetting and dispersing.

SUGGESTED USES:

- ▶ Industrial paints and coating .
- ▶ High quality hammer Paints and top coats Fast dry paints .
- ▶ Fast drying paints.

FORM OF SUPPLY:

% 60 solution in Xylene

SPECIFICATION:

Solid content	: 60 ± 1 %	ASTM D-1259
Type of Oil	: Soya bean oil	
Oil content	: % 29	
Type of Polyol	: mixed of Polyols	
Acid value	: max 10 (mg KOH /g)	ASTM D-1639
Viscosity (25° C) Stock	: 100 – 150	ASTM D-1545
Color (Gardner)	: max 5	ASTM D-1544
Surface drying time	: max 15 minutes	

DILUTABILITY:

Aliphatic	white sprit	limited
Aromatic	Xylene	dilutable
	Toluene	dilutable
Esters	Butyl Acetate	dilutable
	Ethyl Acetate	dilutable
Ketons	Acetone	dilutable
	MEK	dilutable
Alcohols	Buthanol	dilutable
	Ethanol	dilutable



COMPATIBILITY:

Long oil alkyd	Incompatible
Short oil alkyd	Compatible
Medium oil	Compatible
Aliphatic polyIsocyanate	Compatible
Amino resin	Incompatible
Hydroxyl acrylic Resin	Incompatible

STORAGE: This product must be stored in a cool and dry place below 35 °C and away from direct sun light.

PACKAGING: In 200 Kgs. Net steel drums.

DORSA CHEMIE CO. (PAINT & RESINS)
www.dorsachemie.com